



810 Great South Road, Penrose,
Auckland 1061,
New Zealand.
Telephone: 0800 CEMENT (236 368)
E-mail: customer.servicesoffice@goldenbay.co.nz

Test Certificate for Silica Fume: Microsilica SF

Test Report No.: 18#116

Sampling location *GBC Mount Maunganui Service Centre, NZ*
Sample date *07/03/18*
Origin of Silica Fume *Qinghai Province, China.*
Physical form *Fine Grey Powder*
Grade *Densified*

Sample Batch identification: **3049B**

Property	Result	Test Method	AS/NZS 3582.3 Requirements	Testing Authority
Moisture %	0.2	AS 3583.2	3.0 max	GBC Portland
Loss of Ignition %	1.2	AS 3583.3	6.0 max	GBC Portland
SO ₃ %	0.2	AS 3583.8	3.0 max	Cement Australia
SiO ₂ %	96.3	XRF	> 85	SpectraChem Analytical Ltd
Total Alkali Content (Na ₂ O equiv.) %	0.37	XRF	-	SpectraChem Analytical Ltd
Chloride Ion %	0.012	AS 3583.13	-	Cement Australia
Surface Area BET m ² /g	21.8	BET ASTM C1069	-	Auckland University
Strength Index %	123	ASTM C1240	-	Cement Australia

Note: The above samples were tested as received in accordance with methods stated in the AS/NZS 3582.3.

Jim White
Quality System Co-ordinator
GBC Winstone

Date: 15/05/2018