



810 Great South Road, Penrose,
Auckland 1061,
New Zealand.
Telephone: 0800 CEMENT (236 368)
E-mail: customer.servicesoffice@goldenbay.co.nz

Test Certificate for Silica Fume: Microsilica SF

Test Report No.: 18#185

Sampling location *GBC Mount Maunganui Service Centre, NZ*
Sample date *04/04/18*
Origin of Silica Fume *Qinghai Province, China.*
Physical form *Fine Grey Powder*
Grade *Densified*

Sample Batch identification: 3053B Bulk

Property	Result	Test Method	AS/NZS 3582.3 Requirements	Testing Authority
Moisture %	0.3	AS 3583.2	3.0 max	GBC Portland
Loss of Ignition %	0.9	AS 3583.3	6.0 max	GBC Portland
SO ₃ %	0.2	AS 3583.8	3.0 max	Cement Australia
SiO ₂ %	96.4	XRF	> 85	SpectraChem Analytical Ltd
Total Alkali Content (Na ₂ O equiv.) %	0.61	XRF	-	SpectraChem Analytical Ltd
Chloride Ion %	0.019	AS 3583.13	-	Cement Australia
Surface Area BET m ² /g	20.3	BET ASTM C1069	-	Auckland University
Strength Index %	128	ASTM C1240	-	Cement Australia

Note: The above samples were tested as received in accordance with methods stated in the AS/NZS 3582.3.

Jim White
Quality System Co-ordinator
GBC Winstone

Date: 8/08/2018