



CERTIFICATE OF QUALITY

EcoSure® Type GP Cement

NZS3122:2009 (Bulk & Bag Despatch)



Issued to: National Sales Manager

Test Report No: 23#27

info@goldenbay.co.nz

Code	Week Ending / Voyage	Specific Surface Area	Normal Consistency	Initial Set	Final Set	Soundness	Compressive Strength						Free Lime	Sodium Equivalent (NaEq)	Sulphur Trioxide (SO3)	
							ISOECN			Slump	Concrete					
							3 days	7 days	28 days		3 days	7 days				28 days
Mean		342	29.1	140	3:48	1	31.5	44.6	65.3	96	23.2	32.4	49.0	1.8	0.55	2.1
Standard Deviation		13	0.2	11	0:10	0	1.0	1.1	1.6	6	1.8	1.5	2.2	0.3	0.02	0.03
Min		320	28.7	120	3:30	1	29.6	42.6	62.1	90	21.3	30.4	45.4	1.3	0.52	2.1
Max		375	29.5	165	4:15	2	33.9	46.6	68.1	110	26.9	35.7	52.4	2.4	0.58	2.2
NZS 3122:2009 Requirements				45 min	6:00 max	5 max		35.0 min	45.0 min						0.6 max	3.5 max
Units		m2/kg	%	minutes	hrs:mins	mm	MPa	MPa	MPa	mm	MPa	MPa	MPa	%	%	%
230301-330-GP	01/03/23	335	28.9	150	3:45	1	33.9							1.3	0.58	2.1
230225-291-GP	25/02/23	345	28.8	150	3:45	1	32.5			100	21.8			1.4	0.58	2.1
230223-005-GP	23/02/23	340	29.1	150	3:45	1	32.3	45.4						1.5	0.58	2.2
230221-003-GP	21/02/23	345	28.9	165	3:45	1	32.5	46.3		100	21.5	33.3		1.4	0.58	2.2
230216-805-GP	16/02/23	360	28.9	150	3:45	1	31.5	45.2		90	22.3	32.7		1.4	0.57	2.1
230209-635-GP	09/02/23	350	29.1	150	3:45	1	31.7	44.9						1.7	0.58	2.2
230205-361-GP	05/02/23	340	28.8	150	3:45	1	31.3	44.4		90	24.9	30.6		1.6	0.57	2.1
230201-210-GP	01/02/23	345	28.7	135	4:00	1	31.8	46.1	65.1	100	26.9	32.1	51.5	1.6	0.55	2.1
230124-814-GP	24/01/23	345	29.2	120	3:45	1	32.6	46.0	68.1	90	25.8	30.4	48.3	1.4	0.55	2.1
230121-657-GP	21/01/23	325	28.8	120	4:00	1	30.3	45.8	66.4					2.3	0.53	2.1
230119-477-GP	19/01/23	325	29.3	135	4:15	1	30.1	44.6	67.1	90	22.7	32.4	46.7	1.8	0.53	2.1
230113-325-GP	13/01/23	345	29.1	150	3:45	1	31.6	46.6	65.1					1.9	0.55	2.2
230107-315-GP	07/01/23	345	29.1	150	3:45	2	30.8	42.7	65.5	110	21.7	32.0	52.4	1.8	0.53	2.2
221231-208-GP	31/12/22	335	29.3	135	4:00	1	30.3	43.2	62.4	90	22.3	32.1	48.9	1.7	0.52	2.2
221223-021-GP	23/12/22	335	29.4	150	3:45	1	30.3	42.6	66.0	100	21.3	33.3	50.7	2.0	0.53	2.2
221220-706-GP	20/12/22	320	29.5	135	4:00	1	30.9	44.4	67.6					1.8	0.52	2.2
221217-703-GP	17/12/22	325	29.5	135	4:00	1	32.9	44.6	65.1	90	23.4	32.1		1.8	0.54	2.2
221214-374-GP	14/12/22	340	28.9	135	3:45	1	29.6	43.9	66.4					1.9	0.54	2.1
221212-372-GP	12/12/22	335	28.8	120	3:30	1	31.1	43.2	65.2					2.2	0.56	2.1
221207-951-GP	07/12/22	340	29.0	135	4:00	1	32.2	44.9	65.0					2.1	0.57	2.1
221205-949-GP	05/12/22	340	29.2	135	3:45	1	32.3	44.5	65.3	100	22.5	30.5	45.4	2.2	0.57	2.1
221130-529-GP	30/11/22	360	29.2	135	3:45	1	31.3	43.9	65.4	90	25.0	35.7	48.7	2.2	0.55	2.2
221128-527-GP	28/11/22	355	29.1	135	4:00	2	31.5	44.1	64.6					2.3	0.55	2.2
221126-234-GP	26/11/22	375	29.0	135	3:30	1	30.5	44.3	62.9	100	22.7	34.6	48.5	2.4	0.57	2.2
221124-236-GP	24/11/22	355	29.1	135	3:30	1	31.1	43.3	62.1					2.4	0.55	2.1

The above samples were tested as received in accordance with the current terms of accreditation and methods stated in NZS 3122:2009 with the exception of:

Chemical composition to ASTM C114-18

- Concrete Compressive Strength test results outside the scope of accreditation

Sample Retested

This Report must not be reproduced except in full

M. Adler

Michael Adler
Quality Manager



Portland Works, Portland, Whangarei 0178



Date issued: 9/03/2023

Page 1 of 3



EcoSure® Type GP Cement

Compressive Strength ISO-CEN Mortar (Bulk Dispatch)





EcoSure® Type GP Cement

Compressive Strength Concrete (Bulk Dispatch)



—x— 28 Days —■— 7 Days —◆— 3 Days —x— Slump

