SILICA FUME



Nº 455, 456

810 Great South Road, Penrose, Auckland 1061, New Zealand.

Telephone: 0800 CEMENT (236 368) E-mail: order@goldenbay.co.nz

Test Certificate for Silica Fume: Silica Fume Supplied to Market 10kg Bags February & March 2023 Test Report No.: 23#46

Sampling location GBC Mount Maunganui Service Centre, NZ

Sample date 10/01/23

Origin of Silica Fume *Qinghai Province, China.*

Physical form Fine Grey Powder

Grade Densified

Date: 01/05/2023

Sample Batch identification: Batch MPO 33 10kg Bags

Property	Result	Test Method	AS/NZS 3582.3 Requirements	Testing Authority
Moisture %	0.5	AS 3583.2	3.0 max	GBC Portland
Loss on Ignition %	3.7	AS 3583.3	6.0 max	GBC Portland
SO₃ %	0.3	AS 3583.8	3.0 max	Cement Australia
SiO₂%	91.7	XRF	> 85	Cement Australia
Total Alkali Content (Na2O equiv.) %	0.57	XRF	-	Cement Australia
Chloride Ion %	0.037	AS 3583.13	-	Cement Australia
Surface Area BET m²/g	18.6	BET ASTM C1069	-	Auckland University
Strength Index %	131	ASTM C1240	-	Cement Australia

Note: The above samples were tested as received in accordance with methods stated in the AS/NZS 3582.3.

Note: Auckland University is not IANZ Accredited for the BET Surface Area test.

Vincent Lane

Works Chemist Golden Bay Cement